

26 OCT 2004

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
27 November 2003 (27.11.2003)

PCT

(10) International Publication Number
WO 03/097745 A1(51) International Patent Classification⁷: C08L 83/04,
101/10, 69/00

(21) International Application Number: PCT/US03/15331

(22) International Filing Date: 15 May 2003 (15.05.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/381,654 16 May 2002 (16.05.2002) US

(71) Applicants (for all designated States except US): DOW CORNING CORPORATION [US/US]; 2200 West Salzburg Road, Midland, MI 48686-0994 (US). DOW CORNING TORAY SILICONE CO., LTD. [JP/JP]; 4th Floor, AIG Building, 1-1-3, Marunouchi, Chiyoda-ku, Tokyo 100-0005 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ROMENESKO, David [US/US]; 4102 Elm Court, Midland, MI 48642 (US). SCHMIDT, Randall [US/US]; 813 Honeysuckle Circle, Midland, MI 48642 (US). TOGASHI, Atsushi [JP/JP]; 3-7-15-303 Nobuto, Cho-ku, Chiba-shi, Chiba Prefecture 260-0032 (JP). WIEBER, Gary [US/US]; 4407 Huron Drive, Midland, MI 48642 (US).

(74) Common Representative: DOW CORNING CORPORATION; TROY, Timothy, Patent Department - Mail CO1232, 2200 West Salzburg Road, Midland, MI 48686-0994 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,

GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 03/097745 A1

(54) Title: FLAME RETARDANT COMPOSITIONS

(57) Abstract: This invention relates to a flame retardant composition comprising: (a) 81 to 99.99 weight percent of a thermoplastic resin, thermoset resin, thermoplastic resin blend, or thermoset resin blend which upon burning forms a char and (b) 0.01-19 weight percent of a silsesquioxane resin having a weight average molecular weight of greater than 300 and having the average molecular formula: $(R_3SiO_{1/2})_a(R_2SiO_{2/2})_b(RSiO_{3/2})_c(SiO_{4/2})_d(RO_{1/2})_e(OH_{1/2})_f$ wherein each R is hydrogen, an alkyl group, an alkenyl group, or an aryl group having from 6 to 12 carbon atoms, a and b are zero or positive numbers and the value of a+b is greater than zero, c is a positive number, d, e and f are zero or positive numbers with the provisos that the copolymer comprises at least 40 mole percent of $R_3SiO_{3/2}$ units, the copolymer comprises less than 10 mole percent $SiO_{4/2}$ units, greater than 30 mole percent of the silicon-bonded R groups are silicon-bonded aryl groups, greater than 0.5 mole percent of the silicon-bonded R groups are silicon-bonded hydrogen atoms, the content of silicon-bonded hydroxyl groups is equal to or less than 2 weight percent, and the content of silicon-bonded alkoxy groups where the alkoxy group is methoxy or ethoxy is equal to or less than 5 weight percent.

10 / 512733

WO 03/097745

PCT/US03/15331


FLAME RETARDANT COMPOSITIONS

DESCRIPTION

Phenyl silsesquioxane resins are well known in the art as attractive non-halogen fire
5 retardants for aromatic containing thermoplastics such as polycarbonate. However, they
currently must be used with a Teflon® additive to prevent dripping during initial burn in
order to successfully meet desired UL 94 V0 status. The Teflon® additive, a halogen-
containing material, not only adds cost but also reduces transparency of clear thermoplastics
such as polycarbonate. It has been discovered that silicon-bonded hydrogen-containing
10 phenyl silsesquioxane resins provide UL94 VO status to polycarbonate without the use of
Teflon® enabling a transparent non-halogen solution to this need. In addition, these materials
harden the char and thus lower the rate of heat release, of char forming polymers such as
polyesters including polycarbonate, polybutylene terephthalate (PBT), polycyclomethylene
terephthalate (PCT), polyethylene terephthalate (PET), polymers such as polyether sulphone
15 (PES), polyphenylene sulfide (PPS), polyphenylene ether (PPE), and phenolics, nitrogen
containing polymers such as thermoplastic urethanes (TPUs) and polythalamides among
others.

The patents and publications that form the background art for this invention are
EP 1 026 204 A2, Japanese Patent Publication No. 2000212460 A, Japanese Patent
20 Publication No. 11140294 A, Japanese Patent Publication No. 2000226527 A, Japanese
Patent Publication No. 2001031771 A2, EP 0 918 073 A2, Japanese Patent Publication No.
10139996 A, EP 0 829 521 A1, Japanese Patent Publication No. 2000302961 A, PCT Patent
Publication No. WO99/28387, Japanese Patent Publication No. 11217494 A2, Japanese
Patent Publication No. 2001152004 A2, Japanese Patent No. 3048738 B2, PCT Patent
25 Publication No. WO99/40158, U.S. Patent No. 5,100,958, EP 1 094 093 A2,
EP 1 127 921 A1, NEC Publication Polymers Advanced Technology Vol. 9, pages 593-600
(1998), and NEC Publication NEC Research. & Development Vol. 39, No. 2, April 1998.

This invention relates to a flame retardant composition comprising: (a) 81 to 99.99
weight percent of a thermoplastic resin, thermoset resin, thermoplastic resin blend, or
30 thermoset resin blend which upon burning forms a char and (b) 0.01 to 19 weight percent of a
silsesquioxane resin having a weight average molecular weight of greater than 300 and
having the average molecular formula:



wherein each R is hydrogen, an alkyl group, an alkenyl group, or an aryl group having from 6 to 12 carbon atoms, a and b are zero or positive numbers and the value of a+b is greater than zero, c is a positive number, and d, e and f are zero or positive numbers with the provisos that
 5 the copolymer comprises at least 40 mole percent of $RSiO_{3/2}$ units, the copolymer comprises less than 10 mole percent $SiO_{4/2}$ units, greater than 30 mole percent of the silicon-bonded R groups are silicon-bonded aryl groups, greater than 0.5 mole percent of the silicon-bonded R groups are silicon-bonded hydrogen atoms, the content of silicon-bonded hydroxyl groups is equal to or less than 2 weight percent, and the content of silicon-bonded alkoxy groups where
 10 the alkoxy group is methoxy or ethoxy is equal to or less than 5 weight percent.

Component (a) is a thermoplastic resin, thermoset resin, thermoplastic resin blend, or thermoset resin blend which upon burning forms a residue (char). This char is improved by using Component (b), to be harder and thus lower the rate of heat release due to less fuel evolving per unit time during burning. Ideally, the char would ceramify to a glass and
 15 "insulate" the surface from the external flux and other ignition sources and thus have a lower Heat Release Rate.

Component (a) can be a thermoplastic resin exemplified by polycarbonates, polyamides exemplified by Nylons such as polycaprolactam (Nylon-6), polylauryllactam (Nylon-12), polyhexamethylenedipamide (Nylon-6,6), and
 20 polyhexamethylenedodecanamide (Nylon-6,12), and blends of Nylons with other polymers, polyesters exemplified by polybutylene terephthalate (PBT), polyethylene terephthalate (PET), and polyethylene naphthalate (PEN), blends of polycarbonates with other polymers as exemplified by polycarbonate-acrylonitrile-butadiene-styrene (PC/ABS) blends and polycarbonate-polybutylene terephthalate (PC/PBT) blends, polyphenylene ether (PPE),
 25 polyphenyleneoxide (PPO), and blends of PPE or PPO with styrenics such as HIPS, polystyrene, acrylonitrile-butadiene-styrene (ABS), SAN, polyphenylene sulfide (PPS), polyether sulphone (PES), polyaramids, polyimides, phenyl-containing resins having a rigid rod structure, styrenic materials exemplified by ABS (acrylonitrile-butadiene-styrene), polystyrene (PS), and high-impact polystyrene (HIPS), polyacrylates, styrene-acrylonitrile
 30 resins (SAN), halogenated plastics exemplified by polyvinyl chloride, fluoroplastics, and any other halogenated plastics, polyketones, polymethylmethacrylate (PMMA), thermoplastic

elastomers such as thermoplastic urethanes, thermoplastic vulcanizates, and styrene ethylene butylene styrene (SEBS) copolymer, and natural products such as cellulose, rayon, and polylactic acid. Component (a) can also be a blend of any of the thermoplastic resins described above.

- 5 Component (a) can also be a thermoset material. The thermoset material exemplified by epoxy resins, phenolic resins, urethane elastomers, and blends thereof, and also includes any thermoset material which involves mixing one component with another allowing curing to make a thermoset material and component (b) is therein.

10 In the formula for Component (b), R can be a hydrogen atom, an alkyl group exemplified by methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, decyl, and dodecyl, an alkenyl group exemplified by vinyl, allyl, butenyl, pentenyl, hexenyl, octenyl, and decenyl, or an aryl group having from 6 to 12 carbon atoms exemplified by phenyl, naphthyl, methylphenyl, ethylphenyl, chlorophenyl, bromophenyl and fluorophenyl.

Component (b) can thus be selected from

- 15 $(\text{Me}_2\text{HSiO}_{1/2})_a(\text{PhMeSiO}_{2/2})_b(\text{Me}_2\text{SiO}_{2/2})_b(\text{PhSiO}_{3/2})_c$,
 $(\text{MeHSiO}_{2/2})_b(\text{PhSiO}_{3/2})_c$, or
 $(\text{Me}_3\text{SiO}_{1/2})_a(\text{MeHSiO}_{2/2})_b(\text{PhSiO}_{3/2})_c$.

20 The copolymer comprises at least 40 mole percent of $\text{RSiO}_{3/2}$ units, with copolymer typically comprising from 60 mole percent to 90 mole percent of $\text{RSiO}_{3/2}$ units. The copolymer comprises less than 10 mole percent $\text{SiO}_{4/2}$ units, and typically the copolymer will comprise less than 5 mole percent of $\text{SiO}_{4/2}$ units. Greater than 30 mole percent of the silicon-bonded R groups are silicon-bonded aryl groups and typically from 50 to 80 mole percent of the silicon-bonded R groups are silicon-bonded aryl groups. Greater than 0.5 mole percent of the silicon-bonded R groups are silicon-bonded hydrogen atoms, with the mole percent of silicon-bonded R groups that are silicon-bonded hydrogen atoms typically being
25 from 1 to 5 mole percent. The content of silicon-bonded hydroxyl groups is equal to or less than 2 weight percent, and is typically from 0.5 to 1.2 weight percent. The content of silicon-bonded alkoxy groups where the alkoxy group is methoxy or ethoxy is equal to or less than 5 weight percent.

- 30 The siloxane resin of Component (b) is prepared by methods well known in the art such as those described, for example, in the *Silicone Handbook*, Chapters 12 and 13 (pp 466-

515) edited by Kunio Ito (Nikkan Kogyo Shinbun-sha (1990)). These methods include the hydrolysis of mixtures containing the corresponding chlorosilanes or alkoxysilanes and continuing the reaction until the desired molecular weight is achieved.

5 The flame retardant compositions of this invention can further comprise a sodium-containing catalyst. The sodium-containing catalyst is exemplified by organosodium materials such as sodium toluene sulfonate, or sodium stearate. The amount of catalyst used can be from 0.005 to 2 weight percent, but generally comprise from 0.01 to 0.05 weight percent, said weight percent being based on the total weight of the composition.

10 The flame retardant compositions of this invention can further comprise polytetrafluoroethylene powder (TEFLON®) or Dyneon®TF PTFE). The flame retardant compositions of this invention may comprise up to 10 weight percent of polytetrafluoroethylene powder, but generally comprise from 1 to 3 weight percent of polytetrafluoroethylene powder, said weight percent being based on the total weight of the composition. The flame retardant compositions of this invention are useful as clear housings
15 for electronic devices such as computer monitors or housings, should the compositions be clear. Otherwise the compositions are useful as fire resistant compositions in a variety of electronic devices. Relatively low loadings of polytetrafluoroethylene powder were used in the examples disclosed here to maintain moderate to high clarity.

The Fire Test in the Examples hereinbelow was the test described by Underwriters
20 Laboratories Corporate Headquarters 333 Pfingsten Road Northbrook, IL 60062-2096 USA (UL94). A description of the test is included by reference to UL.

An additional fire test, ASTM E 1354, described by American Society for testing and Materials 1916 Race St, Philadelphia, PA 19103. A description of the test is included by reference to the ASTM.

25 Ingredients:

Thermoplastic Resins:

CALIBRE® 200-22 (polycarbonate resin)

MAGNUM® 941 (acrylonitrile-butadiene-styrene resin), and

PELLETHANE® 2355-75A (polyurethane elastomer resin)

30 all which are available from The Dow Chemical Company, Midland, Michigan.

TEFLON® 6C (polytetrafluoroethylene powder made by E. I. DuPont de Nemours of Wilmington, Del.)

EMERGE® 8500 (translucent, ignition resistant polycarbonate available from The Dow Chemical Company, Midland, Mi.).

AMOCO® 4018 (Polypropylene homopolymer, having a density of 0.906 g/cc and a melt flow index of 13.5, Amoco Oil Company Corporation, Chicago, Ill.)

- 5 CRASTIN® 6129 (thermoplastic polyester resin made by E. I. du Pont de Nemours and Company Wilmington Delaware).

ELTESOL ST-90 (sodium toluene sulfonate available from Albright & Wilson Company).

This was used as the Char Catalyst in the Examples below.

- The masterbatches containing the siloxane resin were prepared using each of the
10 resins below with the following formulation:

Masterbatch	Formulation
Thermoplastic Resin or	
Thermoplastic Resin Blend	balance to 100 weight percent
Silsesquioxane Resin	8, 10 or 50 weight percent
15 Char Catalyst	Zero or 0.3 weight percent
Polytetrafluoroethylene Powder	Zero or 3.0 weight percent

Procedure for preparing Masterbatch:

- Heat Haake bowl to 220 °C or about 50°C above T_g (glass transition temperature) of the
20 candidate plastic or blend.

Place Thermoplastic Resin or Thermoplastic Resin Blend into the bowl and bring it to a melt using 100 rpm mixing.

Place Silsesquioxane Resin in bowl, mix for about 2 minutes.

Add Char Catalyst.

- 25 Add Polytetrafluoroethylene Powder (if desired) and mix 5 minutes.

Remove Masterbatch cool and powder/pelletize in chopper.

The Masterbatch was then mixed with the appropriate thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder.

UL 94 Fire Test Specimens

Injection molded 3.2 mm bars and a 4X4 inch 1 mm thick plaque. The plaques were cut to 0.5-inch wide rectangular specimens and the edges sanded to minimize fibrils.

5 Fire Testing

UL 94 Fire Test described above.

ASTM E 1354 Fire Test Specimens

Injection molded 4X4 inch X 3/16-inch thick (100x100x9.75 mm) plaque.

Fire Testing

- 10** ASTM E 1354 Fire Test described above administered at 90 kW/m² cone external heat flux on a Dark Star model Cone Calorimeter software modified by Fire Testing Technology Limited P.O. Box 116, East Grinstead, West Sussex, RH19 4FP, United Kingdom.

Example 1

- 15** Masterbatch containing a silsesquioxane resin having the average molecular formula $(\text{Me}_2\text{HSiO}_{1/2})_{0.20} (\text{PhSiO}_{3/2})_{0.78} (\text{PhMeSiO}_{2/2})_{0.01} (\text{Me}_2\text{SiO}_{2/2})_{0.01}$ where Me denotes methyl and Ph denotes phenyl.

- Isopropanol (559.5 g) was added to phenyltrichlorosilane (1970.8 g), then diluted with toluene (1924.7 g). This mixture was added to heated (to a temperature of 50 °C) deionized
- 20** water (6737.4 g) and the resulting reaction mixture heated to 65 °C for one hour. The aqueous phase was removed and the organic phase washed with deionized water and saturated aqueous NaHCO₃. To facilitate the final separation, additional toluene (1082 g) was added. Residual water was removed from the organic phase via azeotropic distillation and the reaction product concentrated to a ~ 65 wt% solution. Dimethylchlorosilane
- 25** (450.1 g) was added to a portion of this solution (1500.1 g) and the mixture heated to 35 °C for 4.5 hours, then stirred at ambient temperature for three days. Volatiles (250 g) were removed by distillation, then isopropanol (150 g) and toluene (480 g) added. Additional volatiles (668 g) were removed by distillation. Deionized water (97.5 g), dimethoxyethane (500 g) and toluene (160 g) were added, then all volatile materials removed by distillation at
- 30** ambient pressure, then under reduced pressure. The hot molten product was poured onto a

cooled metal surface. The resulting product was isolated as a friable solid. The product was identified by ^{29}Si NMR as a silsesquioxane resin having the average molecular formula: $(\text{Me}_2\text{HSiO}_{1/2})_{0.20}(\text{PhSiO}_{3/2})_{0.78}(\text{PhMeSiO}_{2/2})_{0.01}(\text{Me}_2\text{SiO}_{2/2})_{0.01}$ where Me denotes methyl and Ph denotes phenyl. This silsesquioxane resin was then used to prepare a Masterbatch according to the procedure outlined above. The Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent char catalyst, was then mixed with a thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

Example 2

Masterbatch containing a silsesquioxane resin having the average molecular formula $(\text{MeHSiO}_{2/2})_{0.25}(\text{PhSiO}_{3/2})_{0.75}$ where Me denotes methyl and Ph denotes phenyl.

Phenyltrimethoxysilane (813.5 g) was hydrolyzed with deionized water (346.7 g) in the presence of trifluoromethanesulfonic acid (2.03 g). Volatile material (1006.2 g) was removed via distillation. After cooling to 50 °C, toluene (892.4 g) and additional deionized water (173.3 g) were added. Additional volatile material was removed via distillation to a reaction mixture temperature of 75 °C. Additional toluene (671.9 g), methylhydrogen cyclic siloxanes $(-\text{MeHSiO})_x$ (404.5 g), and glacial acetic acid (404.5 g) were sequentially added and the reaction mixture stirred at 75 °C for five hours, then washed with deionized water, aqueous NaHCO_3 and more deionized water. Residual water in the organic phase azeotropically removed, then the organic solvent removed by stripping under reduced pressure to yield 2915.5 grams of a solid material. The solid material was identified by ^{29}Si NMR as a silsesquioxane resin having the average molecular formula: $(\text{MeHSiO}_{2/2})_{0.25}(\text{PhSiO}_{3/2})_{0.75}$ where Me denotes methyl and Ph denotes phenyl. This silsesquioxane resin was then used to prepare a Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent char catalyst, according to the procedure outlined above. The Masterbatch was then mixed with the thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded

according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

Example 3

5 Masterbatch containing a silsesquioxane resin having the average molecular formula $(\text{Me}_3\text{SiO}_{1/2})_{0.10}(\text{MeHSiO}_{2/2})_{0.19}(\text{PhSiO}_{3/2})_{0.71}$ where Me denotes methyl and Ph denotes phenyl.

Phenyltrimethoxysilane (396 g) was reacted with water (54 g) in the presence of toluene (300 g) and trifluoromethanesulfonic acid (0.2 g) and heated to 70 °C. Volatiles were removed via distillation at this temperature over a three-hour period. Additional toluene (300 g) and methylhydrogen cyclic siloxanes (34 g) were added and the mixture held at 70 °C for an additional three hours. Hexamethyldisiloxane (24 g) was added with additional heating at 70 °C for an additional two hours. After cooling, NaHCO_3 (2 g) was added and the mixture washed three times with water (1500 g total). Volatiles were stripped at 50°C under reduced pressure to produce a white solid product (310 g). The white solid product was identified by ^{29}Si NMR as a silsesquioxane resin having the average molecular formula: $(\text{Me}_3\text{SiO}_{1/2})_{0.10}(\text{MeHSiO}_{2/2})_{0.19}(\text{PhSiO}_{3/2})_{0.71}$ where Me denotes methyl and Ph denotes phenyl. This silsesquioxane resin was then used to prepare a Masterbatch according to the procedure outlined above. The Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent of char catalyst, was then mixed with the thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

Example 4

About 3 weight percent of Polytetrafluoroethylene Powder was added to the Masterbatch prepared in Example 1 with polycarbonate as the plastic resin. This Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent of char catalyst, was then mixed with thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

10

Example 5

About 3 weight percent of Polytetrafluoroethylene Powder was added to the Masterbatch prepared in Example 2 with polycarbonate as the plastic resin. This Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent char catalyst, was then mixed with thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

Example 6

About 3 weight percent of Polytetrafluoroethylene Powder was added to the Masterbatch prepared in Example 3 with polycarbonate as the plastic resin. This Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent char catalyst, was then mixed with thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

Comparison Example 1

Masterbatch containing $(\text{Me}_2\text{HSiO}_{1/2})_{0.22}(\text{PhSiO}_{3/2})_{0.54}(\text{PrSiO}_{3/2})_{0.23}$ where Me denotes methyl, Ph denotes phenyl, and Pr denotes propyl.

- 5 A phenyl propyl silicone resin in solid flake form (1000 g) was dissolved in toluene (667 g), heated to remove residual water via azeotropic distillation, and cooled to ambient temperature. Dimethylchlorosilane (490 g) was added to the solution and the mixture heated to 39°C for three hours, then stirred at ambient temperature for 18 hours. Volatile material was removed until the head temperature reached 110 °C, then the mixture cooled to 30 °C.
- 10 Water (45.8 g) was added and removed via azeotropic distillation, additional water (100 g) added and azeotropically removed, then isopropanol (88 g) added and all volatiles removed by distillation at ambient, then reduced, pressure. The hot molten material was poured onto a cooled metal surface. A portion of the resulting friable solid (502.2 g) was dissolved in dimethoxyethane (500.1 g) and mixed with dimethylchlorosilane (72.3 g). The mixture was
- 15 heated to 35 °C for four hours, then concentrated under reduced pressure to a viscous liquid. Additional dimethoxyethane (310.1 g) and deionized water (50.0 g) were added and all volatiles removed under reduced pressure. Again, dimethoxyethane (199.9 g) and deionized water (39.7 g) were added and heated to reflux for 90 minutes, then all volatiles removed under reduced pressure. The hot molten product was poured onto a cooled metal surface.
- 20 The resulting product was isolated as a friable solid. The product was identified by ^{29}Si NMR as a silsesquioxane resin having the average molecular formula: $(\text{Me}_2\text{HSiO}_{1/2})_{0.22}(\text{PhSiO}_{3/2})_{0.54}(\text{PrSiO}_{3/2})_{0.23}$ where Me denotes methyl, Ph denotes phenyl, and Pr denotes propyl. This silsesquioxane resin was then used to prepare a Masterbatch according to the procedure outlined above. The Masterbatch, produced with 8
- 25 weight percent of the candidate resin and 0.3 weight percent of char catalyst, was then mixed with the thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

30

Comparison Example 2

A Masterbatch, with polycarbonate as the plastic resin, was prepared using the procedure outlined above using Toshiba XC99-B5664 (a siloxane resin having the average molecular formula $(\text{Me}_3\text{SiO}_{1/2})_{0.121}(\text{Me}_2\text{SiO}_{2/2})_{0.157}(\text{PhSiO}_{3/2})_{0.578}(\text{MeSiO}_{3/2})_{0.145}$ where Me denotes methyl and Ph denotes phenyl) as the Siloxane Resin. This Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent of char catalyst, was then mixed with thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

Comparison Example 3

Masterbatch containing $(\text{Me}_3\text{SiO}_{1/2})_{0.188}(\text{PhSiO}_{3/2})_{0.812}$ where Me denotes methyl and Ph denotes phenyl.

A mixture of phenyltrichlorosilane (720.1 g) and trimethylchlorosilane (92.8 g) were hydrolyzed with a mixture of water (640 g) and toluene (519.9 g) cooled in an ice bath. The reaction mixture was heated to 80 °C for 3 hours, then 90°C for 18 hours. Aqueous sodium chloride, additional toluene and a small amount of methanol were added to facilitate the phase removal of the aqueous phase. The portion of mixture that was not readily phase separating was filtered and the organic layers combined and heated to 66 °C for 40 minutes. This was washed sequentially with saturated aqueous NaHCO_3 and aqueous NaCl . Residual water was removed via azeotropic distillation. The product mixture was again filtered, then solvent removed by stripping under reduced pressure and the hot molten product was poured onto a cooled metal surface. The resulting product was isolated as a friable solid. The product was identified by ^{29}Si NMR as a silsesquioxane resin having the average molecular formula: $(\text{Me}_3\text{SiO}_{1/2})_{0.188}(\text{PhSiO}_{3/2})_{0.812}$ where Me denotes methyl and Ph denotes phenyl. This silsesquioxane resin was then used to prepare a Masterbatch according to the procedure outlined above with polycarbonate as the plastic resin. The Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent of char catalyst, was then mixed with the thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of

10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

5

Comparison Example 4

About 3 weight percent of Polytetrafluoroethylene Powder was added to the Masterbatch prepared in Comparison Example 3. This Masterbatch, produced with 8 weight percent of the candidate resin and 0.3 weight percent char catalyst, was then mixed with thermoplastic resin at a weight ratio of thermoplastic resin to Masterbatch of 10:1 in a twin-screw extruder, molded according to the UL 94 test piece procedure and subjected to UL94 Flame Test. The final formulation is shown in Table 1 below. The results are shown in Table 2 below.

10

Table 1
Final Formulation

Example	Thermoplastic Resin (balance to 100 wt%)	Wt% Silsesquioxane Resin	Wt% Char Catalyst	Wt% Teflon 6C
1	CALIBRE® 200-22	0.8	0.03	0.0
2	“	0.8	0.03	0.0
3	“	0.8	0.03	0.0
4	“	0.8 ^a	0.03	0.3
5	“	0.8 ^b	0.03	0.3
6	“	0.8 ^c	0.03	0.3
CE1	“	0.8	0.03	0.0
CE2	“	0.8	0.03	0.0
CE3	“	0.8	0.03	0.0
CE4	“	0.8 ^d	0.03	0.3

^a same silsesquioxane resin as used in example 1

5

^b same silsesquioxane resin as used in example 2

^c same silsesquioxane resin as used in example 3

^d same silsesquioxane resin as used in comparative example 3

Table 2

FR Additive*	Flame Time (seconds)			Cotton Ignition	UL 94 Rating
	Set 1	Set 2	Total 1+2		
Example 1	22	17	39	Y	2
Example 2	11	18	29	N	0
Example 3	15	14	29	Y	2
Example 4	36	41	77	N	0
Example 5	7	17	24	Y	2
Example 6	9	20	29	N	0
Comparison Example 1	105	16	121	Y	2
Comparison Example 2	57	41	98	Y	2
Comparison Example 3	51	37	88	Y	2
Comparison Example 4	44	56	100	Y	2
Emerge® 8500*	30	47	77	Y	2

* test sample dimension 125 x 13 x 1 mm

Examples 7-26 and Comparison Examples 5-9

A Masterbatch containing 10 or 50 weight percent of a silsesquioxane resin having the average molecular formula $(\text{MeHSiO}_{2/2})_{0.25}(\text{PhSiO}_{3/2})_{0.75}$ where Me denotes methyl and Ph denotes phenyl were produced according to the procedure outlined above. The specific thermoplastic resin used in the fire test is described in Table 2 below and was mixed with the Masterbatch in a 10:1 weight ratio mixture of thermoplastic resin to Masterbatch in a twin-screw extruder. The final formulation is shown in Table 3 below. All of these Fire Retarded experiments were performed using ASTM E 1354 with an external heat flux at 90 kW/m^2 . In Table 3, a negative number denotes a reduction of Fire Retardant feature (an improvement) when compared to the virgin resin or blend. For example, the Heat Release Rate is reduced (negative) and is a slower burning fire, thus improved. In Comparison Examples 5-9, non-char forming materials, the Heat Release Rate is positive, thus not an improvement. By virgin, it is meant that the candidate plastic resin is not altered in any way before the burn. It is simply injection molded into the plaques described. The virgin blend is simply the mixture of polycarbonate blended with ABS, PBT, etc. at 85 wt% polycarbonate and 15 wt% blended polymer, also unaltered and molded.

Table 3

Example	Thermoplastic or Thermoset Resin Type (balance to 100 wt %)	Wt% silsesquioxane resin	Wt% Char Catalyst	Wt% Teflon 6C	Delta Avg HRR- Control	Delta Peak Heat Release	Delta Peak CO Release kg/kg	Delta Peak CO2 Releas
7	PELLETHANE® 2355-75A	1	0.03	0.3	-110	-944	-0.0084	-3.8
8		1	0.00	0.0	-24	-768.5	-0.07255	-6.2
9		5	0.03	0.3	-692	-1443	0.28825	-0.8
10		5	0.00	0.0	-286.5	-690.5	-0.6248	-17.3
11		Virgin			0	0	0	
12	CALIBRE® 200-22 (85%)	1	0.03	0.3	-478.5	-738	0.3825	7.0
13	CRASTIN® 6129 (15%)	1	0.00	0.0	-243.5	-630.5	8.9275	180.
14		5	0.03	0.3	-535	-1013.5	0.3635	7.
15		5	0.00	0.0	-437	-720	2.54675	61.
16		Virgin blend			0	0	0	
	CALIBRE® 200-22 (85%)							
17	MAGNUM® (15%)	1	0.03	0.3	-1002.5	-521	0.195	2.
18		1	0.00	0.0	-1405.5	-1638	1.0455	20.
19		5	0.03	0.3	-1036	-657	2.4795	28.
20		5	0.00	0.0	-189	-46	0.20545	4.
21		Virgin blend			0	0	0	
22	CRASTIN® 6129	1	0.03	0.3	-131	-585.5	-1.1642	-43.1
23		1	0.00	0.0	-2694	4200	-1.6595	-54.
24		5	0.03	0.3	-1033	-1500	1.5329	-52.
25		5	0.00	0.0	662	141.5	-1.375	-46.
26		Virgin			0	0	0	
Comparison Example 5	AMOCO® 4018	1	0.03	0.3	514	57.5	-0.35315	-1.5
Comparison Example 6		1	0.00	0.0	233	768.5	8.11185	174.4
Comparison Example 7		5	0.03	0.3	1893	2125.5	-0.34365	1.7
Comparison Example 8		5	0.00	0.0	248.5	332.5	2.08335	35.5
Comparison Example 9		Virgin			0	0	0	


The examples of the invention provide thermoplastics with excellent flame retardant behavior without the use of Polytetrafluoroethylene Powder (Teflon®) halogen-containing additives. Addition of Polytetrafluoroethylene Powder to the flame retarded compositions of this invention in some cases further improved the flame retardant and UL94 behavior of the compositions of this invention.

CLAIMS

1. A flame retardant composition comprising:

(a) 81 to 99.99 weight percent of a thermoplastic resin, thermoset resin, thermoplastic resin blend, or thermoset resin blend which upon burning forms a char; and

(b) 0.01-19 weight percent of a silsesquioxane resin having a weight average molecular weight of greater than 300 and having the average molecular formula:



wherein each R is hydrogen, an alkyl group, an alkenyl group, or an aryl group having from 6 to 12 carbon atoms, a and b are zero or positive numbers and the value of a+b is greater than zero, c is a positive number, d, e and f are zero or positive numbers with the provisos that the copolymer comprises at least 40 mole percent of $RSiO_{3/2}$ units, the copolymer comprises less than 10 mole percent $SiO_{4/2}$ units, greater than 30 mole percent of the silicon-bonded R groups are silicon-bonded aryl groups, greater than 0.5 mole percent of the silicon-bonded R groups are silicon-bonded hydrogen atoms, the content of silicon-bonded hydroxyl groups is equal to or less than 2 weight percent, and the content of silicon-bonded alkoxy groups where the alkoxy group is methoxy or ethoxy is equal to or less than 5 weight percent.

2. A composition according to Claim 1, wherein (a) is selected from polycarbonates, polyamides, polyesters, blends of polycarbonates with other polymers, polyphenylene ether, polyphenyleneoxide, blends of polyphenylene ether with styrenics, blends of polyphenyleneoxide with styrenic materials, polyaramids, polyimides, phenyl-containing resins having a rigid rod structure, styrenic materials, polyacrylates, styrene-acrylonitrile resins, halogenated plastics, polyketones, polymethylmethacrylate (PMMA), thermoplastic elastomers, cellulotics, rayon, or polylactic acid.

3. A composition according to Claim 2, wherein the styrenic materials are selected from acrylonitrile-butadiene-styrene, polystyrene, or high-impact polystyrene.

3. A composition according to Claim 1, wherein (a) is selected from polycarbonates, polycaprolactam, polylauryllactam, polyhexamethylenedipamide, polyhexamethylenedodecanamide, blends of Nylons with other polymers, polybutylene terephthalate, polyethylene terephthalate, polyethylene naphthalate, polycarbonate-acrylonitrile-butadiene-styrene blends, polycarbonate-polybutylene terephthalate blends, polyphenylene ether, polyphenyleneoxide, polyphenylene sulfide, polyether sulphone, polyethylene sulfide, acrylonitrile-butadiene-styrene, polystyrene, high-impact polystyrene, styrene-acrylonitrile resins, polyvinyl chloride, fluoroplastics, polymethylmethacrylate, thermoplastic urethanes, thermoplastic vulcanizates, or styrene ethylene butylene styrene copolymer.

5. A composition according to Claim 1, wherein (a) is selected from epoxy resins, phenolic resins, urethane elastomers, or blends thereof.

15

6. A composition, according to Claim 1, wherein each R is a hydrogen atom, methyl, or phenyl.

7. A composition according to Claims 1, 2, or 4, wherein the copolymer comprises 60 to 90 mole percent of $\text{RSiO}_{3/2}$ units, less than 5 mole percent of $\text{SiO}_{4/2}$ units, 50 to 80 mole percent silicon-bonded phenyl groups, 1 to 5 mole percent silicon-bonded hydrogen atoms, 0.5 to 1.2 weight percent silicon-bonded hydroxyl groups, and less than 5 percent silicon-bonded alkoxy groups where the alkoxy group is methoxy or ethoxy.

8. A composition according to Claims 1, 2, 3, 4, or 5, wherein (b) is $(\text{Me}_2\text{HSiO}_{1/2})_a(\text{PhMeSiO}_{2/2})_b(\text{Me}_2\text{SiO}_{2/2})_c(\text{PhSiO}_{3/2})_c$, $(\text{MeHSiO}_{2/2})_b(\text{PhSiO}_{3/2})_c$, or $(\text{Me}_3\text{SiO}_{1/2})_a(\text{MeHSiO}_{2/2})_b(\text{PhSiO}_{3/2})_c$.

9. A composition according to Claims 1, 2, 4, or 5, wherein the compositions further comprise a sodium-containing catalyst.

10. A composition according to Claims 1, 2, 4, 5, or 9, wherein the compositions
5 further comprise polytetrafluoroethylene powder.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 03/15331

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L83/04 C08L101/10 C08L69/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2001/018486 A1 (LICHTENHAN JOSEPH D ET AL) 30 August 2001 (2001-08-30) the whole document ---	1-10
A	EP 0 936 250 A (DOW CORNING) 18 August 1999 (1999-08-18) examples ---	1-10
A	US 5 904 791 A (BEARINGER CLAYTON R ET AL) 18 May 1999 (1999-05-18) examples ---	1-10
A	US 3 615 272 A (COLLINS WARDE T ET AL) 26 October 1971 (1971-10-26) the whole document --- -/-	1-10

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

22 July 2003

Date of mailing of the international search report

29/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kollitz, R

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/15331

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
T	US 6 518 357 B1 (CAMPBELL JOHN ROBERT ET AL) 11 February 2003 (2003-02-11) claims; examples; tables 1,2 ---	1-10
A	EP 0 604 130 A (GE PLASTICS JAPAN LTD) 29 June 1994 (1994-06-29) claims; examples ---	1-10
A	US 5 484 867 A (LICHTENHAN JOSEPH D ET AL) 16 January 1996 (1996-01-16) the whole document -----	1-10

INTERNATIONAL SEARCH REPORT

 International Application No
 PCT/US 03/15331

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2001018486	A1	30-08-2001	NONE
EP 0936250	A	18-08-1999	US 5972512 A 26-10-1999 BR 9900654 A 26-12-2000 CN 1232057 A 20-10-1999 DE 69901357 D1 06-06-2002 DE 69901357 T2 12-12-2002 EP 0936250 A2 18-08-1999 JP 11279407 A 12-10-1999
US 5904791	A	18-05-1999	DE 69606942 D1 13-04-2000 DE 69606942 T2 05-10-2000 EP 0764704 A1 26-03-1997 JP 9130065 A 16-05-1997
US 3615272	A	26-10-1971	CA 917883 A1 02-01-1973 DE 1955511 A1 06-05-1970 FR 2022525 A5 31-07-1970 GB 1245483 A 08-09-1971
US 6518357	B1	11-02-2003	AU 6855201 A 15-04-2002 WO 0228970 A1 11-04-2002
EP 0604130	A	29-06-1994	JP 3263795 B2 11-03-2002 JP 6192556 A 12-07-1994 DE 69314297 D1 06-11-1997 DE 69314297 T2 09-04-1998 EP 0604130 A2 29-06-1994 ES 2107633 T3 01-12-1997 US 5352747 A 04-10-1994
US 5484867	A	16-01-1996	US 5412053 A 02-05-1995 US 5589562 A 31-12-1996